



NWEF149861


Exterior Clear Water Base 1K Sealer

TECHINCAL FEATURES

- High Solids, Easy To Apply, Easy to Sand
- Great Exterior Durability
- Excellent Flow, High Coverage, Suited for Vertical Hang
- Contains UV Filters, Extreme Outdoor Resistance
- For Use as a Base under any NOVALK Water Base Exterior Top Coat



GOOD TO KNOW



NOVOTINT

NWEF149861 can be used as a Clear base for the creation of pigmented colors, thanks to our Novotint Software.



PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.



WHERE TO USE

Recommended for exterior doors, windows, and outdoor furniture.



MEETS OR EXCEEDS KCMA STANDARDS



- Heat and humidity test
- Cold check test
- Chemical resistance test
- Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NWEF149861	Clear Waterborne 1K Exterior Sealer.	05/01/2025

Recommended Use	Recommended for exterior doors, windows, and outdoor furniture.	
Application	Apply using airless, air assisted airless, or conventional spray. 1-2 coats at 10-12 Wet Mills can be applied under any of the NOVALK water base topcoats. Sanding between coats using 320 or very fine grit.	
Mixing Preparation	NWEF149861B is a ready to use product. To increase resistance of the film, use NCW99 (iso-free) @ 5% (volume). If needed, add warm water up to 5% by volume to improve flow. Agitate well.	
Solids % by Wt.	37%	
Voc.	30.014 G/L	
Density	1.05	
Pot Life	N/A	
Shelf Life	12 Months	
Dry Times	Approximate Drying Times At 10-12 Wet Mills	
Dust Free	15 Minutes	Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 12 mils dry film.
Handling	60 Minutes	
OverCoat	2-4 Hours	
Stackable	24 Hours	

Notes And Remarks:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41- 95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.