

NA1051-XX Clear PU TopCoat





- Exceptional Silky Smooth Clear Top Coat
- High Solids, Easy To Apply, Fast Dry, Great Vertical Hang
- Mar And Moisture / Chemical Resistance

GOOD TO KNOW



NA1051 can be used as a clear base for the creation of pigmented colors, thanks to our Novotint Software.

Novotint

Where to use it

Recommended for kitchen

cabinets, dining, living, and

bedroom furniture.



For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

Proper Care

Meets or exceeds KCMA Standards.





Cold check test



Chemical resistance test













Available in 5 through 90 sheen







361 W Longview AVE Mansfield, OH 44903 Phone: 419-983-0007 Email: info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NA1051-XX	Clear PU Top Coat	08/01/2024
Recommended Use Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furni		Furniture / Fixtures
Application	APPLY USING AIR ASSISTED AIRLESS, OR CONVENTION IF A BASE COAT IS DESIRED USE NF14901 SEALI 2-3 TOTAL COATS RECOMMENDED, AT 4-5 WET N SANDING WITH 320 OR VERY FINE GRIT BETWEEN O	ER MILS,
Mixing Preparation 50% NC935 Catalyst 20%-30% Reduction with ND4028 Reducer		er
Solids % by Wt	40%	
Voc.	658.38 G/L	
Density	.93	
Pot Life	4 Hour	
Shelf Life	24 Months	
Dry Times Dust Free Handling OverCoat Stackable	Approximate Drying Times At 4-5 Wet Mils 15 Minutes At 4-5 Wet Mils Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 6 mils dry film.	

Notes And Remarks:

- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.

Technical service tel: +419-983-0007 Email: info@novalkusa.com