



NAH15939B-XX

White Conversion Varnish Top Coat

TECHINCAL FEATURES

- Exceptional Silky Smooth White Conversion Varnish Top Coat
- High Solids, Easy To Apply, Fast Dry, Great Vertical Hang
- Formulated Using Melamine Resins For Exceptional Hardness
- Excellent Mar, Moisture And Chemical Resistance
- Virtually Formaldehyde Free
- Available in 5 through 90 Sheen



**NOVOTINT
2.0**



GOOD TO KNOW

SPRAY CANS

NAH15939B Series CV can be used to fill spray cans for touchups.




PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

NOVOTINT

NAH15939B can be used as White base, Or for the creation of pigmented colors
Thanks to our NovoTint Software.



WHERE TO USE IT

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test



Cold check test



Chemical resistance test



Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NAH15939B	ACID CATALYZED WHITE TOPCOAT	05/01/2025

Recommended Use	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture	
Application	APPLY USING AIR ASSISTED AIRLESS, OR CONVENTIONAL SPRAY. IF A BASE COAT IS DESIRED USE NFH15920B CV PRIMER 2-3 TOTAL COATS RECOMMENDED, AT 4-5 WET MILS, SANDING WITH 320 OR VERY FINE GRIT BETWEEN COATS.	
Mixing Preparation	10% (volume) NCH999 Acid Catalyst. NAH15939B is a ready to use product. 10%-20% (volume) reduction with ND5303 (slow), ND4028 (medium) or ND5920 (fast) may be added to improve flow.	
Solids % by Wt.	52%	
Voc.	565.14 g/l	
Density	1.16	
Pot Life	12 Hour	
Shelf Life	12 Months	
Dry Times	Approximate Drying Times At 4-5 Wet Mils	
Dust Free	20 Minutes	Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 6 mils dry film.
Handling	45 Minutes	
OverCoat	120 Minutes	
Stackable	12 Hours	

Notes And Remarks:

- It is not recommended to apply amino-ureic topcoats like this one on top of polyurethane. If the curing process is not complete, defects may appear.
- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.