

GOOD TO KNOW

Novotint



NFC14935 can be used as a transparent base for the creation of pigmented colors, thanks to our Novotint Software.

Where to use it



Recommended for kitchen cabinets, dining, living, and bedroom furniture.

419) 983-0007

Proper Care

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

Meets or exceeds KCMA Standards.

Heat and humidity test



Cold check test



Chemical resistance test



Film swell test











361 W Longview AVE Mansfield, OH 44903 Phone: 419-983-0007 Email: info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NFC14935	Clear AcrylicSealer	05/01/2025

Recommended Use	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures		
Application	APPLY USING AIR ASSISTED AIRLESS, OR CONVENTIONAL SPRAY. TO BE USED UNDER NOVALK ACRYLIC COATINGS 2-3 TOTAL COATS AT 4-5 WET MILS RECOMMENDED, SANDING WITH 320 OR VERY FINE GRIT BETWEEN COATS.		
Mixing Preparation	Mix 5% (volume) with NC119 Acrylic Catalyst 30%-60% reduction with ND5404 (medium or ND5920 (fast) dependent on environmental and shop conditions.		
Solids % by Wt.		38%	
Voc.	692.62 G/L		
Density	.93		
Pot Life	4 Hour		
Shelf Life	24 Months		
Dry Times	Approximate Drying Times At 4-5 Wet Mils		
Dust Free	10 Minutes	Note:	
Handling	30 Minutes	Drying times may vary depending on thickness applied, temperature and/or humidity.	
OverCoat	90 Minutes	Warning:	
Stackable	12 Hours	Total film thickness of the finish should not exceed 6 mils dry film.	

Notes And Remarks:

- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.

Technical service tel: +419-983-0007 Email: info@novalkusa.com