



NFH15900

Pre-Cat Clear Sealer

TECHINCAL FEATURES

- Great For Use On MDF & Wood, High Coverage, Easy Sanding
- High Solids, Easy To Apply, Fast Dry, Great Vertical Hang
- Formulated Using Melamine Resins For Exceptional Hardness
- Virtually Formaldehyde Free



GOOD TO KNOW

SPRAY CANS

NAH15901 can be used to fill spray cans for touchups.

NOVOTINT

NFH15900 can be used as Clear base, Or for the creation of pigmented colors
Thanks to our NovoTint Software.

WHERE TO USE IT

Recommended for kitchen cabinets, dining, living, and bedroom furniture.

PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test

Cold check test

Chemical resistance test

Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NFH15900	PRE CATALYZED CLEAR SEALER	05/01/2025
Recommended Use	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures	
Application	APPLY USING AIR ASSISTED AIRLESS, OR CONVENTIONAL SPRAY. TO BE USED UNDER NOVALK PRE-CAT TOPCOATS 2-3 TOTAL COATS RECOMMENDED, AT 4-5 WET MILS, SANDING WITH 320 OR VERY FINE GRIT BETWEEN COATS.	
Mixing Preparation	30%-50% (volume) reduction with ND5303 (slow), ND4028 (medium) or ND5920 (fast) dependent on environmental and shop conditions.	
Solids % by Wt.	26%	
Voc.	701.026 G/L	
Density	.95	
Pot Life	NA	
Shelf Life	12 Months	
Dry Times	Approximate Drying Times At 4-5 Wet Mils	
Dust Free	10 Minutes	Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 6 mils dry film.
Handling	25 Minutes	
OverCoat	90 Minutes	
Stackable	12 Hours	

Notes And Remarks:

- It is not recommended to apply amino-ureic primers like this one on top of polyurethane. If the curing process is not complete, defects may appear.
- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.