

NFH15970

Pre-Cat Clear Sealer

TECHINCAL FEATURES

- Great For Use On MDF & Wood, High Coverage, Easy Sanding
- High Solids, Easy To Apply, Fast Dry, Great Vertical Hang
- Formulated Using Melamine Resins For Exceptional Hardness
- Virtually Formaldehyde Free



**NOVOTINT
2.0**



GOOD TO KNOW

SPRAY CANS

NFH15970 pre-cat can be used to fill spray cans for touchups.




PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

NOVOTINT

NFH15970 can be used as Clear base, Or for the creation of pigmented colors thanks to our NovoTint Software.



WHERE TO USE IT

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test

Cold check test

Chemical resistance test

Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

| Code | Description | Date |
|---------------------------|--|--|
| NFH15970 | PRE CATALYZED CLEAR SEALER | 05/01/2025 |
| Recommended Use | Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures | |
| Application | APPLY USING AIR ASSISTED AIRLESS, OR CONVENTIONAL SPRAY. TO BE USED UNDER NOVALK PRE-CAT TOPCOATS 2-3 TOTAL COATS RECOMMENDED, AT 4-5 WET MILS, SANDING WITH 320 OR VERY FINE GRIT BETWEEN COATS. | |
| Mixing Preparation | NFH15970 is a ready to use product. 10%-20% (volume) reduction with ND5303 (slow), ND4028 (medium) or ND5920 (fast) may be added to improve flow, if necessary. | |
| Solids % by Wt. | 29% | |
| Voc. | 701.026 G/L | |
| Density | .94 | |
| Pot Life | NA | |
| Shelf Life | 12 Months | |
| Dry Times | Approximate Drying Times At 4-5 Wet Mils | |
| Dust Free | 10 Minutes | Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 6 mils dry film. |
| Handling | 25 Minutes | |
| OverCoat | 90 Minutes | |
| Stackable | 12 Hours | |

Notes And Remarks:

- It is not recommended to apply amino-ureic primers like this one on top of polyurethane. If the curing process is not complete, defects may appear.
- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.