

NAC16064-XX


Anti-Scratch HS Clear Acrylic Top Coat

TECHINCAL FEATURES

- Exceptional Silky Smooth Clear Acrylic Top Coat
- High Solids, Easy To Apply, Fast Dry, Great Vertical Hang
- Excellent Mar, Moisture & Chemical Resistance
- Available in 5 through 90 sheen



GOOD TO KNOW



Novotint

NAC16064-XX can be used as a transparent base for the creation of pigmented colors, thanks to our Novotint Software.



Proper Care

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

Meets or exceeds KCMA Standards.

Heat and humidity test



Cold check test



Chemical resistance test



Film swell test



Where to use it

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NAC16064-XX	Anti-Scratch HS Clear AcrylicTop Coat	05/01/2025

Recommended Use	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures	
Application	APPLY USING AIR ASSISTED AIRLESS, OR CONVENTIONAL SPRAY. IF A SEALER COAT IS DESIRED USE NFC14935 ACRYLIC SEALER. 2-3 TOTAL COATS RECOMMENDED @ 4-5 wet mils, SANDING WITH 320 OR VERY FINE GRIT BETWEEN COATS.	
Mixing Preparation	mix 10% (volume) with NC119 Acrylic Catalyst 30-60% (volume) reduction with ND5404 (medium) or ND5920 (fast) dependent on environmental and shop conditions.	
Solids % by Wt.	38%	
Voc.	674.89 G/L	
Density	.95	
Pot Life	6 Hour	
Shelf Life	24 Months	
Dry Times	Approximate Drying Times At 4-5 Wet Mils	
Dust Free	15 Minutes	Note: Drying times may vary depending on thickness applied, temperature and/or humidity. Warning: Total film thickness of the finish should not exceed 6 mils dry film.
Handling	30 Minutes	
OverCoat	90 Minutes	
Stackable	12 Hours	

Notes And Remarks:

- The curing process of this product is greatly improved by heat/oven curing.
- To achieve a good pot-life, please keep any unused mixture away from air by covering the container with a lid or plastic.
- Thinner selection and ambient temperature will directly influence the pot-life.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.