

# NWIA149910

Clear Water Base 1K/2K Self-Sealer Top Coat





- Natural Effect, Zero Sheen
- Does **NOT** change the Natural Color of the Wood
- Superb Silky-Smooth Touch
- Wax Effect, Beeswax Aroma, Food Safe



## **GOOD TO KNOW**



#### **NOVOTINT**

NWIA149910 is a clear topcoat ONLY but can be applied to stains or pigmented colors.



#### **PROPER CARE**

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.



#### WHERE TO USE

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



### **MEETS OR EXCEEDS KCMA STANDARDS**



**Heat and humidity test** 

Cold check test

Chemical resistance test

Film swell test















361 W Longview AVE Mansfield, OH 44903 Phone: 419-983-0007 Email: info@novalkusa.com

#### **TECHNICAL DATA SHEET**

Code	1	Description		
NWIA149910	Clear Water Base Top	Coat 1K / 2K Beeswax Natural Effect	05/01/2025	
Recommended U	SE Kitchen & Bathroom C	nen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures		
Application		Apply using airless, air assisted airless, conventional spray, brush or roller.  2 coats @ 2-4 Wet Mils recommended, sanding with 320 or very fine grit between coats.		
Mixing Preparati	I	NWIA149910 is a ready to use product. To increase resistance of the film, use NCW80 or NCW99 (iso-free) @ 5% (volume). Agitate well. Can be reduced up to 10% (volume) with warm water.		
Solids % by Wt		21%		
Voc.		30.014 G/L		
Density	1.02			
Pot Life		3 Hour		
Shelf Life		12 Months		
Dry Times	Approximate Dryin	Approximate Drying Times At 2-4 Wet Mils		
Dust Free	15 Minutes	Note:		
Handling	45 Minutes	Drying times may vary depending on thickness applie temperature and/or humidity.  Warning:	thickness applied,	
OverCoat	4 Hours			
Stackable	12 Hours	Total film thickness of the finish shou exceed 6 mils dry film.	ld not	

#### **Notes And Remarks:**

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41-95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.

Technical service tel: +419-983-0007 Email: info@novalkusa.com