



NWIA149921B


White Water Base 1K / 2K Self-Sealing Top Coat

TECHINCAL FEATURES

- Excellent Hardness
- Good Chemical Resistant Properties
- Exceptional Silky Smooth Touch
- Easy To Apply, Fast Dry, Great For Production
- Available in 5 through 90 sheen



GOOD TO KNOW



NOVOTINT

NWIA149921B can be used as a white base for the creation of pigmented colors, thanks to our Novotint Software.



PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.



WHERE TO USE

Recommended for kitchen cabinets, dining, living, and bedroom furniture.



MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test

Cold check test

Chemical resistance test

Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description	Date
NWIA149921B	White Water Base Self Seal Top Coat 1K / 2K. Indoor use.	05/01/2025

Recommended Use	Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures	
Application	<p>Apply using airless, air assisted airless, or conventional spray, brush or roller. If a base coat is desired use NWIF179917B White Water Base Primer. 2-3 coats recommended @ 4-6 wet mils,</p> <p>sanding with 320 or very fine grit between coats.</p> <p>Brush/Roll: add NU1034 WB flow additive @ 5-10% (volume).</p> <p>Brush then back roll with foam/mohair roller.</p>	
Mixing Preparation	NWIA149921B is a ready to use product. To increase resistance of the film, use NCW80 or NCW99 (iso-free) @ 5% (volume). Agitate well.	
Solids % by Wt.	38%	
Voc.	30.014 G/L	
Density	1.15	
Pot Life	3 Hour	
Shelf Life	12 Months	
Dry Times	<p>Note: Approximate Drying Times At 4-6 Wet Mils</p> <p>Drying times may vary depending on thickness applied, temperature and/or humidity.</p>	
Dust Free	15 Minutes	<p>Warning:</p> <p>Total film thickness of the finish should not exceed 6 mils dry film.</p>
Handling	30 Minutes	
OverCoat	1 Hours	

Notes And Remarks:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41- 95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.