

NWIF149539 Clear Water Base

Clear Water Base
1K or 2K Sealer





TECHINCAL FEATURES

- High Transparency, High Solids
- Fast Drying, Easy to Apply
- Excellent Sanding Sealer, Great Vertical Hang
- To Be Used Under Novalk Water Base Top Coats Where Sanding Sealer is Desired.

GOOD TO KNOW



NOVOTINT

NWIF149539 can be used as a transparent base for the creation of pigmented colors, thanks to our Novotint Software.



WHERE TO USE

Recommended for kitchen cabinets, dining, living, and bedroom furniture.





PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

MEETS OR EXCEEDS KCMA STANDARDS



419) 983-0007

Heat and humidity test

Cold check test

Chemical resistance test

Film swell test















361 W Longview AVE Mansfield, OH 44903 Phone: 419-983-0007 Email: info@novalkusa.com

TECHNICAL DATA SHEET

Code	Description Date
NWIF149539	Clear Water Base Sealer 1K / 2K. Indoor use. 05/01/2025
Recommended U	SE Kitchen & Bathroom Cabinetry, Residential / Commercial Wood Furniture / Fixtures
Application	Apply using airless, air assisted airless, or conventional spray, brush or roller. Apply under any of the Novalk WB topcoats. 1-2 coats recommended @ 4-5 wet mils, sanding between coats using 320 or very fine grit. Brush/Roll: add NU1034 WB flow additive @ 5-10% (volume). Brush then back roll with foam/mohair roller.
Mixing Preparation	NWIF149539 is a ready to use product. To increase resistance of the film, use NCW80 or NCW99 @ 5% (volume). Agitate well.
Solids % by Wt.	32%
Voc.	0.0 G/L
Density	1.07
Pot Life	2 Hour
Shelf Life	12 Months
Dry Times Dust Free Handling OverCoat	Approximate Drying Times At 4-5 Wet Mils 15 Minutes Orying times may vary depending on thickness applied temperature and/or humidity. 2-4 Hours Warning: Total film thickness of the finish should not exceed 6 mils dry film.
Notes And Remarks	:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41-95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- · Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.

Technical service tel: +419-983-0007 Email: info@novalkusa.com