



# NWEA149885B

## Exterior White Water Base 1K Self-Sealing Top Coat

### TECHINCAL FEATURES


- Great Exterior Durability, Up to 5 Years When using 3 Coats
- Excellent Flow, High Solids, Great Vertical Hang
- Contains UV Filters, Extreme Outdoor Resistance
- Available in 15 through 90 sheen



**NOVOTINT  
2.0**



### GOOD TO KNOW



#### NOVOTINT

NWEA149855B can be used as a white base for the creation of pigmented colors, thanks to our Novotint Software.



#### PROPER CARE

For cleaning purposes use mild soap and warm water. Furniture polishes not recommended.

#### WHERE TO USE

Recommended for Exterior Doors, Windows, & Outdoor Furniture



### MEETS OR EXCEEDS KCMA STANDARDS



Heat and humidity test

Cold check test

Chemical resistance test

Film swell test



361 W Longview Ave, Mansfield, OH 44903



(419) 983-0007



Info@novalkusa.com

## TECHNICAL DATA SHEET

Code	Description	Date
NWEA149885B	Exterior White Water Base Self-Seal 1K Top Coat. Outdoor Use.	05/01/2025

<b>Recommended Use</b>	Exterior Wood Furniture, Cabinetry, Doors & Windows.	
<b>Application</b>	Apply using airless, air assisted airless, or conventional spray. Apply 1 coat of NOVO-SHIELD impregnating agent followed by 2-3 coats of NWEA149885, at 10-12 Wet Mils, sanding with 320 or very fine grit between coats.	
<b>Mixing Preparation</b>	Ready to be applied. Can be reduced with 5% of warm water	
<b>Solids % by Wt.</b>	42%	
<b>Voc.</b>	0.0 G/L	
<b>Density</b>	1.15	
<b>Pot Life</b>	3 Hour	
<b>Shelf Life</b>	12 Months	
<b>Dry Times</b>	Approximate Drying Times At 10-12 Wet Mils	
<b>Dust Free</b>	15 Minutes	<b>Note:</b> Drying times may vary depending on thickness applied, temperature and/or humidity.  <b>Warning:</b> Total film thickness of the finish should not exceed 6 mils dry film.
<b>Handling</b>	60 Minutes	
<b>OverCoat</b>	2-4 Hours	
<b>Stackable</b>	24 Hours	

### Notes And Remarks:

- Mix the product before use.
- The shelf life is 12 months if the products are stored at temperature between 41 - 95°F.
- The product application must be done at a temperature no less than 53°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. Novalk guarantees the physical-chemical characteristics of its products, as well as their consistency. However, the responsibility for the final result of the product application is to be considered up to the user, who must ensure that the selected product corresponds to his application needs and to the type of support selected. The viscosity level of highly thixotropic products may differ from what is reported in the technical data sheet. To be considered acceptable, this value should differ by a maximum of 30% from the reported value in the technical data sheet.